

# TECHNICAL FEATURES

MODEL: <b>CR.ARNO ANTIC</b>
SIZE: <b>60x120</b>
THICKNESS(mm): <b>10.5</b>
DATE: <b>10/07/2021</b>
CODE: <b>004.869.0203.04040</b>
GROUP: <b>GROUP BIa UNE-EN 14411 Annex G / SASO ISO 13006:2018 Annex G</b>
TILE TYPE: <b>GL</b>
FINISH: <b>LEVIGLASS</b>
FAMILY: <b>LEVIGLASS-POLISHED GLAZED RECTIFIED PORCELAIN TILES</b>
NUMBER OF DESIGNS:



**SKU: T11025**

TEST	RESULT	
<b>UNE-EN ISO 10545-2</b> DIMENSIONAL FEATURES	<b>COMPLIES WITH THE STANDARD</b>	
<b>UNE-EN ISO 10545-3</b> WATER ABSORPTION	<b>≤ 0,5 %</b>	
<b>UNE-EN ISO 10545-4</b> MODULUS OF RUPTURE N/mm <sup>2</sup>	<b>1600-2400 N</b>	
	BREAKING STRENGTH <b>35-45 N/mm<sup>2</sup></b>	
<b>UNE-EN ISO 10545-6</b> RESISTANCE TO DEEP ABRASION (MM <sup>3</sup> )	<b>&lt; 130 mm<sup>3</sup></b>	
<b>UNE-EN ISO 10545-7</b> RESISTANCE TO SURFACE ABRASION	<b>PEI IV</b>	
<b>UNE-EN ISO 10545-8</b> LINEAR THERMAL EXPANSION	<b>&lt;7,0 x 10<sup>-6</sup> °C<sup>-1</sup></b>	
<b>UNE-EN ISO 10545-9</b> THERMAL SHOCK RESISTANCE	<b>RESISTS</b>	
<b>UNE-EN ISO 10545-11</b> CRAZING RESISTANCE	<b>RESISTS</b>	
<b>UNE-EN ISO 10545-12</b> FROST RESISTANCE	<b>RESISTS</b>	
<b>UNE-EN ISO 10545-13</b> CHEMICAL RESISTANCE - AMMONIUM CHLORIDE 100 G/L	<b>A</b>	
	CHEMICAL RESISTANCE - SODIUM HYPOCHLORITE 20 MG/L	<b>A</b>
	CHEMICAL RESISTANCE - HYDROCHLORIC ACID 3%	<b>COMPLIES WITH THE STANDARD</b>
	CHEMICAL RESISTANCE - CITRIC ACID 100 G/L	<b>COMPLIES WITH THE STANDARD</b>
	CHEMICAL RESISTANCE - POTASSIUM HYDROXYDE 30 G/L	<b>COMPLIES WITH THE STANDARD</b>
<b>UNE-EN ISO 10545-14</b> STAIN RESISTANCE - GREEN AGENT IN LIGHT OIL	<b>5</b>	
	STAIN RESISTANCE - IODINE SOLUTION IN ALCOHOL	<b>5</b>
	STAIN RESISTANCE - OLIVE OIL	<b>5</b>