

# TECHNICAL FEATURES

MODEL: <b>CR.BELVEDERE IVORY</b>
SIZE: <b>60x60</b>
THICKNESS(mm): <b>9.5</b>
DATE: <b>10/07/2021</b>
CODE: <b>004.840.0164.05758</b>
GROUP: <b>GROUP BIa UNE-EN 14411 Annex G / SASO ISO 13006:2018 Annex G</b>
TILE TYPE: <b>GL</b>
FINISH: <b>LEVIGLASS</b>
FAMILY: <b>LEVIGLASS-POLISHED GLAZED RECTIFIED PORCELAIN TILES</b>
NUMBER OF DESIGNS:



TEST	RESULT
<b>UNE-EN ISO 10545-2</b> DIMENSIONAL FEATURES	<b>COMPLIES WITH THE STANDARD</b>
<b>UNE-EN ISO 10545-3</b> WATER ABSORPTION	<b>&lt;= 0,5 %</b>
<b>UNE-EN ISO 10545-4</b> MODULUS OF RUPTURE	<b>1600-2400 N</b>
	<b>BREAKING STRENGTH</b>
	<b>35-45 N/mm2</b>
<b>UNE-EN ISO 10545-6</b> RESISTANCE TO DEEP ABRASION (MM3)	<b>&lt; 130 mm3</b>
<b>UNE-EN ISO 10545-7</b> RESISTANCE TO SURFACE ABRASION	<b>PEI IV</b>
<b>UNE-EN ISO 10545-8</b> LINEAR THERMAL EXPANSION	<b>&lt;7,0 x 10-6 °C-1</b>
<b>UNE-EN ISO 10545-9</b> THERMAL SHOCK RESISTANCE	<b>RESISTS</b>
<b>UNE-EN ISO 10545-11</b> CRAZING RESISTANCE	<b>RESISTS</b>
<b>UNE-EN ISO 10545-12</b> FROST RESISTANCE	<b>RESISTS</b>
<b>UNE-EN ISO 10545-13</b> CHEMICAL RESISTANCE - AMMONIUM CHLORIDE 100 G/L	<b>A</b>
	<b>CHEMICAL RESISTANCE - SODIUM HYPOCHLORITE 20 MG/L</b>
	<b>A</b>
	<b>CHEMICAL RESISTANCE - HYDROCHLORIC ACID 3%</b>
	<b>COMPLIES WITH THE STANDARD</b>
	<b>CHEMICAL RESISTANCE - CITRIC ACID 100 G/L</b>
	<b>COMPLIES WITH THE STANDARD</b>
	<b>CHEMICAL RESISTANCE - POTASSIUM HYDROXYDE 30 G/L</b>
	<b>COMPLIES WITH THE STANDARD</b>
<b>UNE-EN ISO 10545-14</b> STAIN RESISTANCE - GREEN AGENT IN LIGHT OIL	<b>5</b>
	<b>STAIN RESISTANCE - IODINE SOLUTION IN ALCOHOL</b>
	<b>5</b>
	<b>STAIN RESISTANCE - OLIVE OIL</b>
	<b>5</b>